



DSC402SG2

소재 특성

DESCO™ DSC402SG2는 PBT(Poly Butylene Terephthalate)를 기본으로 한 Glass Fiber & 내충격제 강화 제품으로 전기적 특성 및 기계적 강도가 뛰어난 제품입니다.

적용 분야

DESCO™ DSC402SG2 는 전기적 특성 및 힌지 특성을 요구하는 connector 등의 부품에 적합합니다.

성형 조건

본 제품은 제습 건조 후 밀봉되므로 성형 전 별도 건조과정이 필요 없습니다.

만약 수분이 함유되어 있을 경우에는 최소 120°C 온도에서 2 시간 이상 제습 건조하여 수분 함유율이 0.2% 이하가 될 수 있도록 당부 드립니다.

[추천 성형 조건]

		UNIT	SETTING
수지 건조 온도		°C	120 ~ 140
수지 건조 시간		Hr	2 ~ 5
실린더	후부(이송)	°C	240 ~ 250
	중부(압축)	°C	240 ~ 255
	전부	°C	240 ~ 260
노즐 온도		°C	240 ~ 260
소재 온도		°C	240 ~ 260
금형 온도		°C	50 ~ 100
사출 속도		%	40 ~ 70
사출압력	1 st	%	30 ~ 60
	2 nd	%	30 ~ 60
보압		%	10 ~ 20

안전 자료

당사에서 제공하고 있는 물질안전보건자료(MSDS)를 참고하시기 바랍니다.



DSC402SG2

구분	항목	측정방법	단위	대표치
물리적 성질	수분 흡수율 (24hr water at 23°C)	ASTM D-570	%	-
	비중	ASTM D-792	-	1.3
	성형 수축율 (3t/100Ø 원판)	-	%	0.4~0.6
기계적 성질	인장 강도	ASTM D-638	Kgf/cm ²	700
	파단 신율	ASTM D-638	%	5
	굴곡 탄성률	ASTM D-790	Kgf/cm ²	30,000
	굴곡 강도	ASTM D-790	Kgf/cm ²	1,200
	Izod 충격강도	ASTM D-256	Kgf.cm/cm	7
	로크웰 경도(R-Scale)	ASTM D-785	-	117
열적 성질	융점	DSC	°C	222
	열변형 온도(1.8MPa)	ASTM D-648	°C	190
	열변형 온도(0.46MPa)	ASTM D-648	°C	200
	난연성	UL 94	-	HB
전기적 성질	체적 저항	ASTM D-257	Ohm.mm	-
	유전 상수(10 ⁶ Hz)	ASTM D-150	-	-
	절연 파괴 강도	ASTM D-149	KV/mm	-
	내아크성	ASTM D-495	Sec	-

☞ 제품 분류 code / PBT GF

☞ 위 물성치는 당사에서 시험표준에 의하여 측정한 실험측정치이며 성형제품의 물성을 보증하기 위하여서는 별도의 데이터가 고려되어야 합니다.

This documentation is made out based on our tests and experiments in our R&D center with piled up experience and knowledge. And the values are measured on injection molded test specimens. It is suggested that this information contained in this document can be used for general indication. Therefore, you should not construe it as product specifications, and you should do appropriate test before you considering your conditions for newly applications.