



DSC201G10

소재 특성

DESCO™ DSC201G10는 Polyamide66을 기본으로 Glass Fiber 50% 강화된 제품이며 높은 기계적 강도, 유동성 및 성형성이 뛰어난 제품입니다.

적용 분야

DESCO™ DSC201G10는 높은 기계적 강도, 제진성, 요구되는 Automotive Side Mirror Parts등의 기계, 자동차 부품에 적용 됩니다.

성형 조건

본 제품은 제습 건조 후 밀봉되므로 성형 전 별도 건조과정이 필요 없습니다.

만약 수분이 함유되어 있을 경우에는 최소 80℃ 온도에서 3 시간 이상 제습 건조하여 수분 함유율이 0.2% 이하가 될 수 있도록 당부 드립니다.

[추천 성형 조건]

		UNIT	SETTING
수지 건조 온도		℃	80 ~ 100
수지 건조 시간		Hr	4 ~ 5
실린더	후부(이송)	℃	270 ~ 280
	중부(압축)	℃	280 ~ 285
	전부	℃	285 ~ 290
노즐 온도		℃	280 ~ 285
소재 온도		℃	280 ~ 285
금형 온도		℃	100 ~ 130
사출 속도		%	40 ~ 70
사출압력	1 st	%	30 ~ 60
	2 nd	%	30 ~ 60
보압		%	10 ~ 20

안전 자료

당사에서 제공하고 있는 물질안전보건자료(MSDS)를 참고하시기 바랍니다.



DSC201G10

구 분	항 목	측정방법	단위	대표치
물리적 성질	수분 흡수율 (24hr water at 23°C)	ASTM D-570	%	0.5
	비중	ASTM D-792	-	1.56
	성형 수축율 (3t/100Ø 원판)	-	%	0.3~0.6
기계적 성질	인장 강도	ASTM D-638	Kgf/cm ²	2,250
	파단 신율	ASTM D-638	%	2
	굴곡 탄성률	ASTM D-790	Kgf/cm ²	130,000
	굴곡 강도	ASTM D-790	Kgf/cm ²	3,200
	Izod 충격강도	ASTM D-256	Kgf.cm/cm	15
	로크웰 경도(R-Scale)	ASTM D-785	-	128
열적 성질	융점	DSC	°C	260
	열변형 온도(1.8MPa)	ASTM D-648	°C	260
	열변형 온도(0.46MPa)	ASTM D-648	°C	265
	난 연 성	UL 94	-	HB
	체적 저항	ASTM D-257	Ohm.mm	10 ¹⁵
전기적 성질	유전 상수(10 ⁶ Hz)	ASTM D-150	-	4
	절연 파괴 강도	ASTM D-149	KV/mm	25
	내아크성	ASTM D-495	Sec	105

☞ 제품 분류 code / PA66 GF50

☞ 위 물성치는 당사에서 시험표준에 의하여 측정한 실험측정치이며 성형제품의 물성을 보증하기 위하여서는 별도의 데이터가 고려되어야 합니다.

This documentation is made out based on our tests and experiments in our R&D center with piled up experience and knowledge. And the values are measured on injection molded test specimens. It is suggested that this information contained in this document can be used for general indication. Therefore, you should not construe it as product specifications, and you should do appropriate test before you considering your conditions for newly applications.